

# WATERPROOFING SYSTEM VEHICULAR ROOF NEXA POLYUREA COLD

## NEXA COATINGS


Details and definition of the constructive solution for inclusion in the waterproofing project of intense walkable and vehicular roofs using a cold-applied polyurea liquid membrane, NEXA POLYUREA COLD. Depending on the technical and aesthetic requirements of each project, the system can be implemented using the membranes specified in the attached table.

### Constructive solution for the vehicular system

Waterproofing of the intense walkable roof using a cold-applied polyurea liquid membrane, NEXA POLYUREA COLD, with a dosage of 0.307 to 0.410 lb/ft<sup>2</sup> (1.5-2 kg/m<sup>2</sup>) with reinforcement. The process includes cleaning and preparation of the substrate, priming, treatment of downspouts, expansion joints, intersections, and singular points, in compliance with the manufacturer's technical specifications.

Seal the membrane with an aliphatic polyurethane varnish, NEXA UV PROTECTIVE, pigmented with pastes (max. 10%) with a dosage of 0.102 lb/ft<sup>2</sup> (0.500 kg/m<sup>2</sup>). Add brown corundum (Type 35-50) to the first coat of NEXA UV PROTECTIVE varnish with a dosage of 0.061 - 0.123 lb/ft<sup>2</sup> (0.3-0.6 kg/m<sup>2</sup>).

The performance is 0.307 to 0.410 lb/ft<sup>2</sup>, equivalent to 47.24 mils thickness (1.5-2 kg/m<sup>2</sup> equivalent to 1.2 mm thickness). Apply in 1, 2, or 3 coats.



### MEMBRANES AVAILABLE FOR THE SYSTEM

NEXA POLYUREA

NEXA POLYUREA COLD

1/2

## NEXA COATINGS

C/ Aiguafreda 24  
L'Ametlla del Vallès  
08480 Barcelona Spain

✉ [contact@nexacoatings.com](mailto:contact@nexacoatings.com)  
☎ contact: +34 656 43 74 36  
🌐 [www.nexacoatings.com](http://www.nexacoatings.com)

# WATERPROOFING SYSTEM VEHICULAR ROOF NEXA POLYUREA COLD

## NEXA COATINGS

The adhesion of the material depends on the quality of the substrate. Proper substrate preparation, correct treatment of singular points, and the selection of the most appropriate primer are essential. Below, we outline some key considerations and refer you to the annex, where you can find more detailed information. Please note that these systems and treatments are generic and do not take into account the specific characteristics of each project, so we recommend contacting the technical or commercial support team in your area.

### Substrate Preparation

Analysis and preparation of new or rehabilitated substrates  
Ensure that the surfaces are smooth, clean, dry, and as hard as possible, following the guidelines provided in the "Preparation and Treatment Guide for Singular Points."

Repair surface defects, irregularities, cracks, and gaps using polyurethane sealant. (See [www.nexacoatings.com](http://www.nexacoatings.com))

### Treatment of Singular Points

Intersections with downspouts, expansion joints, sharp edges, coves, mechanical fixations, cable penetrations, edge trims, and border treatments:

These should be addressed using NEXA MASTIC PU polyurethane sealant or mesh, according to the diagrams provided in our "Preparation and Treatment Guide for Singular Points." (See [www.nexacoatings.com](http://www.nexacoatings.com))

### Priming

Depending on the quality, porosity, or nature of the substrate to be coated, or the type of product to be used, it may be necessary to apply, with a consumption of 0.02 to 0.09 lb/ft<sup>2</sup> (0.100 to 0.450 kg/m<sup>2</sup>), one of the following primers: NEXA PRIMER EPOX W or NEXA PRIMER PU 2K. Some waterproofing applications may require a vapor barrier, which can be created with NEXA PRIMER EPOX W (0.12–0.20 lb/ft<sup>2</sup> (0.6–1 kg/m<sup>2</sup>) depending on the substrate's porosity). (See [www.nexacoatings.com](http://www.nexacoatings.com))



2/2

## NEXA COATINGS

C/ Aiguafreda 24  
L'Ametlla del Vallès  
08480 Barcelona Spain

✉ [contact@nexacoatings.com](mailto:contact@nexacoatings.com)  
☎ contact: +34 656 43 74 36  
🌐 [www.nexacoatings.com](http://www.nexacoatings.com)